

PAT

Photographic Activity Test (Per ISO 14523) Research Report

Date: October 21, 2002

Customer: T. Loeters
Company: PapierFabriek Schut BV
Address: Kabeljauw 2
PO Box 1
NL-6866 ZG Heelsum
The Netherlands

Material: 6022-3K

Silver Image Interaction

Density change of control: -0.94
Upper pass/fail limit: -0.75
Density change of material: -0.96
Lower pass/fail limit: -1.13

Density change caused by material must fall between upper and lower limits ($\pm 20\%$ change in control)

Material pass/fail: Pass
Reason: Within image interaction limits

* Control material in Whatman No. 1 filter paper

Gelatin Staining

Density change of control: 0.07
Stain limit: 0.15
Density change of material: 0.11

Staining caused by material must be less than stain limit (control +0.08)

Result: Pass
Reason: Less than stain limit

Mottling of Image Interaction Detector

Visual assessment of uniform action

Result: Pass

Overall Performance - Must pass all criteria: Pass

Note: The PA
Imaging Mate
Filing Enclos

Lomb Memorial D
ent and by RIT's r

Filter Paper Control