

FRISENETTE ApS



PRODUCT SPECIFICATION

Date 1st November 2011

PRODUCT	PPC TS
BASE & THICKNESS	75 µm Polyester film

GENERAL DESCRIPTION: DOUBLE MATT PPC POLYESTER FILM
PRODUCT CODE 6842.

PROPERTIES	TEST METHOD	UNITS	SPEC. VALUES
GENERAL			
Total thickness		micron	95
Relative density (23°C)	ASTM D.1505		1.40
MECHANICAL			
Tensile strength at break	ASTM D.882	daN/mm ²	18
Elongation at break	ASTM D.882	%	130
THERMAL			
Shrinkage 30mn-150°C	ASTM D.1204	%	MD < 0.6 TD < 0.4
SPECIFIC			
Smoothness	TAPPI T.479	Sec.	80
Opacity UV	Internal	%	60
Surface resistivity	ASTM D.257	Ω.cm	10 ¹¹
Whiteness	Internal	%	> 79

MD : Machine Direction

TD : Transverse Direction

All typical values of properties relate to assessment made at time of manufacture.

This specification is confidential and submitted to the other party for mutual agreement